

## WORKSHOP COOL - RED

### PRODUCT DESCRIPTION

Workshop Cool – Red is a Type A ethylene glycol-based coolant, free from NAPS (Nitrites, Amines, Phosphates, Silicates, Borates, and 2-Ethylhexanoic acid). It utilises a premium formulation of organic acid additive (OAT) as an inhibitor package, specifically engineered for use in diesel and petrol vehicles manufactured in Europe and Japan, as well as heavy-duty vehicles for both on and off-road applications, industrial machinery, and agricultural and construction equipment. This coolant is designed to ensure optimum heat transfer, reducing operational temperatures, and providing maximum protection against foaming, rust, corrosion, cavitation, scaling, oxidation, and degradation of the cooling system. It offers a guaranteed protection period of at least 7 years or 500,000 kilometers, whichever comes first. Workshop Cool – Red meets European standards for phosphate-free formulations and Japanese standards for being silicate and 2-Ethylhexanoic acid-free. It is particularly suitable for use in petrol, light and heavy-duty diesel engines, mining equipment, marine vessels, highway vehicles, both on and off-road, and stationary engines in industrial settings where anti-freeze, anti-boil, and anti-corrosion properties are essential. Additionally, it is recommended for motorcycles, construction and agricultural machinery, wind turbines, and solar farms.

#### Usage Instructions:

Workshop Cool – Red should be diluted to a concentration of 50% volume/volume (vv.) with deionized water to ensure freezing protection.

- For automotive applications: Mix at a ratio of 50% vv., offering freezing protection down to -18°C, with a boiling point of 105°C.

### APPLICATIONS & BENEFITS

- Ethylene glycol-based coolant without NAPS.
- Meets AS2108:2004 Type A requirements.
- Contains OAT inhibitor package for diesel/petrol vehicles, heavy-duty machinery.
- Optimal heat transfer protects against foaming, rust, corrosion, scaling, oxidation.
- 7 years/500,000 km protection.
- Meets European phosphate-free, Japanese silicate/2-Ethylhexanoic acid-free standards.
- Compatible with all plastics, rubbers, and seals.
- Suitable for various engines/equipment including motorcycles, wind turbines, solar farms.
- Dilute to 50% vv. with deionized water for freezing protection.

### PACK SIZES AVAILABLE

20L, 205L

### SPECIFICATIONS

- |                           |                     |                               |
|---------------------------|---------------------|-------------------------------|
| • AS 2108:2004 Type A     | • Paccar CSO185     | • John Deere 8650-4           |
| • Fiat 9.55523            | • BAIC Foton Motors | • Saab                        |
| • Opel                    | • Hyundai           | • Case New Holland MAT3620    |
| • AFNOR NFR 15-601 Type I | • Peugeot           | • Komatsu                     |
| • Ford WSS-M97-B44-D      | • Bentley TL774D/F  | • Scania T1.02-98 0813        |
| • ONORM V 5123            | • Jaso 325          | • Caterpillar EC-1            |
| • Atlantis Diesel Engines | • Porsche           | • KSM 2142                    |
| • Freightliner 48-25878   | • BR637             | • Seat TL774-D/F              |
| • Nissan NES M5059        | • JIS K2234         | • Caterpillar MAK A4.05.09.01 |
| • Audi TL 774-D/F         | • Renault 774-D     | • IVECO 18-1830               |
| • GM 1825M/1899M/6277M    | • Bugatti TL774D/F  | • Skoda TL774-D/F             |

The information contained in this Product Data Sheet is accurate at the time of printing and is subject to change without prior notice.

© Vertex is a registered trademark of Vertex Lubricants NZ Ltd.

- CNH MAT 3624/3724
- Lamborghini TL 774-D/F
- Toyota Long Life TSK2601G
- CHRYSLER MS 12106/ MS 7170
- LIEBHERR MD 1-36-130
- VW TL774-D/F
- CUMMINS CES 14603, 14439
- MAN 324 SNF
- Waukesha 4-1974D
- CUNA NC 956-16
- MACK RVI/ MACK 014 GS 17009
- Volvo
- DAF MAT 74002
- MAZDA MEZ MN 121D
- Daihatsu
- MB 325.3
- Detroit Diesel 93K217/Perkins
- Mini Diesel D
- Deutz DQC CB-14
- Mitsubishi ES-X64217
- Deutz AG 0199-99-1115/AG 0199-99-2091
- MTU MTL 5048
- Ferrari (from 2005)
- Navistar

### TYPICAL CHARACTERISTICS

WORKSHOP COOL - RED	METHOD	VALUES
<b>Chemical Nature:</b>	Proprietary Formulation	Type A coolant / organic corrosion inhibitors
<b>Appearance</b>	Visual	Clear Liquid without solid matter
<b>Colour</b>	Visual	Red
<b>Density at 20 °C</b>	DIN5175-3	1.11-1.12 g/cm <sup>3</sup>
<b>Boiling Point @ mix ratio, %, vv. 50</b>	ASTM D1120	105°C
<b>Freezing point @ mix ratio, %, vv. 50</b>	ASTM D1177	-18°C
<b>Reserve Alkalinity, mL</b>	ASTM D1121	3-5
<b>Foam characteristics</b>	ASTM D1188	<50mL/<3s
<b>pH Value</b>	ASTM D1287	7.5-9.5
<b>Miscibility with water</b>	Visual	freely miscible
<b>Hard water stability</b>	Visual	stable, no precipitation
<b>Typical ASTM Corrosion Performance</b>		
<b>Glassware Corrosion Test ASTM D 1384</b>		
<b>Metal and alloy</b>	<b>Weight loss (mg/coupon)</b>	<b>Spec. limit (mg/coupon)</b>
Copper	1	10 max
Solder	0	30 max
Brass	*-1	10 max
Steel	0	10 max
Cast Iron	*-4	10 max
Cast Aluminium	2	30 max
* Negative values mean increase of weight		

### ADDITIONAL INFORMATION

- Product needs to be diluted @ 50% vv.
- Always dispose used coolants in accordance with state regulations
- The products contain Bittering agents.
- Product can be stored for 5 years provided container remains sealed.
- Full System Flush is recommended before using this product.

Designed for New Zealand Conditions | Manufactured from virgin base stocks. For more technical information please contact Vertex Lubricants NZ Technical Dept. +64 9 640 0004. Sheet updated 2 April 2025.